

Description

VitasheetGroup's ViPrint Polypropylene sheets are designed for the graphic arts industry. They are corona treated on both sides and can be printed and decorated using different techniques (Screen or offset printing, embossing, stamping). They include an antistatic treatment to avoid attracting dust. They are offered in a wide range of colours and emboss finish and are often available from stock.

ViPrint Cord 3800: an opaque or translucent, coloured sheet with our cord emboss.

Applications

Packaging, boxes, school and office stationery...

Key Features

Certification/Approvals

Approved grades (depending on colour) are available on request.
Food: European Legislation 2002/72/EC.
TOY: EN 71 Part 3.

Printing

Screen and offset printing on one side (please specify in case of offset printing).

Conversion

Guillotine cutting: Can be cut on traditional printing guillotine with double-edged blade.

Creasing: Cold and hot creasing technique can be used depending on the thickness. The resulting hinges can be folded million of times thanks to the remarkable characteristics of polypropylene.

Welding: Different techniques can be used to weld ViPrint (Thermal (thin gauge), Ultrasonic, Hot Gas).

Gluing: ViPrint can be glued with PUR glue or hot melt, although welding is the preferred option.

Product Availability

Colour

Opaque sheet with 20 standards colours or translucent with 4 standard colours.

Finish

Matt cord/grained G05

Thickness

0.6 mm to 2 mm.

Sheet Size Specifications

Gauge	Sheet sizes	
	Width	Length
0,6 to 0, 8 mm	600/800 mm	900/1600 mm
0,8 to 1 mm	600/800 mm	700/1600 mm
1 mm to 2 mm	600/800 mm	500/1600 mm

NB: available sizes may vary depending on colours/embosses/order size, please ask confirmation to sales department

Physical properties (Guide Only*)

Properties	Unit	Standard	Method	Value
Density	g/cm ³	ISO 1833	-	0.92
Charpy Notched Impact Strength	kJ/m ²	ISO 179	1eA at 23°C	9
Tensile Strength	MPa	ISO 527	50 mm/min	36
Elongation at Break	%	ISO 527	50 mm/min	14
Flexural Modulus	MPa	ISO 178	2 mm/min	850
Elastic Modulus	MPa	ISO 178	50 mm/min	900

*The above properties are based on data given by the polypropylene manufacturer. However due to modifications during the extrusion process, the above data should only be used a rough guide. The density value can change depending upon the type and quantity of pigments or additives used.

Additional Information

Thermoforming

This product is not recommended for thermoforming, as there is a good possibility the sheet may web during the process.

Outdoor/UV Resistance

In outdoor or strong UV light conditions, ViPrint can become brittle in a matter of months. For UV resistance grades please contact the Sales Office.

Storage

This product has been corona treated which is required to allow ViPrint to be printed and glued. It should be noted that it has a limited shelf life, which can be effected by how it is stored. Ideally it should be stored in dark, dry and cool conditions.

Chemical Resistance

Chemical resistance is influenced by many factors, including concentration, temperature, exposure time and material stress. Therefore the data below should only be used as a guide.

Reagent	Chemical resistance	Reagent	Chemical resistance
Acetone	Very good	Beer	Excellent
Acid – (Weak)	Excellent	Brake Fluid	Very good
Acid – (Strong)	Very good	Coffee	Excellent
Alcohol	Very good	Detergent	Excellent
Anti-freeze	Excellent	Diesel	Good
Base (Weak)	Excellent	Foodstuffs	Excellent
Base (Strong)	Good	Lubricating Oil	Good
Battery Acid	Very good	Petrol	Good

Manufacturing Tolerances

SHEET GAUGE	Up to 0.8 mm	0.81 to 2.00 mm
GAUGE	± 0.02 mm	± 0.03 mm
LENGTH*	± 1 mm	± 1 mm
WIDTH*	± 1.5 mm	± 1.5 mm

* Maximum difference between 2 sheets of a same lot.

VitasheetGroup

Charta House
30 - 38 Church Street
Staines
TW18 4EP
www.vitasheetgroup.com

NOTE The information contained in this leaflet is based on our present technical knowledge and experience. In view of the large number of factors that may influence the processing and use of our products, the information does not relieve the processors and manufacturers of the need to carry out their own tests and experiments. Our information does not constitute a legally binding assurance of product availability, of particular properties or of a suitability for a particular end use. Patent rights that may exist must be duly observed.